## **Technical Data**

WildOak
BY TERRA MATER
LakeWood 190mm

Attributes	Result		
Species	European Oak		
Size (L x W x Thickness/top) mm	1900mm x 190mm x 14mm/3mm		
Locking system	5G Välinge		
Pattern	1 strip		
Core	3-layer construction with SPF core		
Edging	Micro bevelled		
Pack size	2.888m <sup>2</sup>		
Pack weight	22kg		
Pack length	1900mm, 8 boards per pack, up to 25% nesting		
Top layer (lamella)	3mm European oak		
Surface finish	8% matte UV lacquer		
Installation	Floating / Direct stick		
Adhesive	Swedish Dynea		
Installation Methods			
Fully bonded	Yes*		
Nailed	No		
Floated underlay	Yes*		
Over under slab heating Yes*			
Subject to compatible subfloor and correct instal	lation (Refer Installation Instructions)		
Test Information & Others			
Origin	Europe		
EUTR	Legally harvested timber		
FSC	Not available		
Janka hardness rating	1360 LBF (7.0)		
Slip testing	AS/NZS 4586-2004 Wet: P3, Dry: D1		
Australian reaction to fire (Floor)	ASISO 9239-1:2003 CRF 3.6kwm <sup>2</sup> , smoke value 19%		

Installati	on & V	Varrantv	/

Warranty (Commercial)

Environmental rating

Warranty (Domestic)

Australian reaction to fire (Wall)

Release of 4-phenylcyclonexene

Release of formaldehyde

Cigarette burns

Total VOC

All LakeWood floors must be installed by a competent approved installer who will have the necessary skills and take individual site circumstance into account. LakeWood warranty will only apply to floors which have been installed according to the Lake Wood installation instructions available in each box of LakeWood and also on the TerraMater website - terramaterfloors.com.au

ASTM D5116 0.016mg/m<sup>2</sup>/hr (max limit allowable 0.5mg/m<sup>2</sup>/hr)

ASTM D51166 0.093mg/m<sup>2</sup>/hr (max limit allowable 0.1) ASTM D5116 <0.004mg/m<sup>2</sup>/hr (max limit allowable 0.05)

A+. Green Building Council of Australia: Pass

20 Year wear and lifetime structural

5 Year wear and lifetime structural

AS/NZS 3837:1998 58.3kw/m<sup>2</sup>

Repairable

Please note this technical sheet was written by TerraMater Pty Ltd, All the information is specifield correctly while writing and publication of the sheet. The company reserves the right to change the specifications of this product at any time withour piror notice to third parties.