Technical Data

Wi]	d	Ο	\mathbf{a}	k
I	BY te	RRA	MA1	ſER
	Orig	ins 22	20n	۱m

Attributes	Result	
Species	European Oak	
Size (L x W x Thickness/top) mm	2200mm X 220mm X 14mm/3mm	
Locking system	Tongue & Groove	
Pattern	1 Strip	
Core	3-layer construction with SPF core	
Edging	4 sided micro bevel	
Pack size	2.904m ²	
Pack weight	23kg	
Pack length	2200mm, 6 boards per pack, up to 16% nesting per pack	
Top layer (lamella)	3mm European Oak	
Surface finish	Super matte UV lacquer 10% gloss	
Installation	Floating / Direct stick	
Adhesive	Swedish Dynea	
Installation Methods		
Fully bonded	Yes*	
Nailed	No	
Floated underlay	Yes*	
Over under slab heating	Yes*	
*Subject to compatible subfloor and correct instal	lation (Refer Installation Instructions)	
Test Information & Others		
Origin	Europe	
EUTR	Legally harvested timber	
FSC	Not available	
Janka hardness rating	1360 LBF (7.0)	
Slip testing	AS/NZS 4586-2004 Wet: P3, Dry: D1	
Australian reaction to fire (Floor)	ASISO 9239-1:2003 CRF 3.6kwm ² , smoke value 19%	
Australian reaction to fire (Wall)	AS/NZS 3837:1998 58.3kw/m ²	
Cigarette burns	Repairable	
Release of formaldehyde	ASTM D51166 0.093mg/m²/hr (max limit allowable 0.1)	

Installation & Warranty

Warranty (Commercial)

Environmental rating

Warranty (Domestic)

Total VOC

Release of 4-phenylcyclonexene

All WildOak floors must be installed by a competent approved installer who will have the necessary skills and take individual site circumstance into account. WildOak warranty will only apply to floors which have been installed according to the WildOak installation instructions available in each box of WildOak and also on the TerraMater website terramaterfloors.com.au

ASTM D5116 <0.004mg/m²/hr (max limit allowable 0.05)

A+. Green Building Council of Australia: Pass

20 Year wear and lifetime structural

5 Year wear and lifetime structural

ASTM D5116 0.016mg/m²/hr (max limit allowable 0.5mg/m²/hr)

Please note this technical sheet was written by TerraMater Pty Ltd, All the information is specifield correctly while writing and publication of the sheet. The company reserves the right to change the specfications of this product at any time withour piror notice to third parties.